

ExperWall CM 20

COLOR OPTIONS: Grey

25

±%2 KG



Plastering and Masonry Mortars

998-2 103725

GÜVEN MADENCİLİK İNŞAAT SAN. ve TİC. A.Ş.

CEMENT BASED, PUMICE ADDED MASONRY MORTAR

Cement based, single component, high quality granulometric pumice and various environmentally friendly chemical additives added, masonry mortar for interior and exterior spaces with high water impermeability coefficient.

**EASY TO
APPLY****RESISTANT TO
CLIMATE
CONDITIONS**

TECHNICAL SPECIFICATIONS

Chemical Structure	Cement based, pumice added powder
Dry Unit Weight	~850-950 g/cm ³
Granulation	0-2 mm
Mixture Ratio	6,00-6,50 lt. water / 25 kg powder
Pot Life	~1-2 hours
Compressive Strength	M5; ≥5 N/mm ² (EN 1015-11)
Bond Strength	≥0,3 N/mm ²
Capillary Water Absorption	0,4 kg/m ²
Water Vapor Permeability	5-35 (EN 1015-19)
Chloride Content	≤%0,10
Mass per Unit Volume of Hardened Mortar	1.000 (±200) (EN 1015-10)
Thermal Conductivity	≤0,33 W/mK (EN 1745)
Drying Time	24 hours
Consumption	3,00-3,50 kg/m ²

* All technical values are calculated at +23°C and 50% relative humidity. Changes in temperature and humidity change the technical values.

ADVANTAGES

- Easy to apply.
- Breathes. It keeps the humidity in the space in balance by allowing the passage of vapor.
- Prevents sound and heat generation.
- Resistant to water, humidity, severe weather conditions and frost.
- Fireproof.

APPLICATION AREAS

Used as a masonry mortar:

- Indoors and outdoors,
- During the application of building elements such as pumice block, stone, brick, briquette, gas concrete, natural stone etc.

SURFACE AND APPLICATION CONDITIONS

- Ambient temperature should be between: +5°C and +35°C .
- Make sure that conditions such as frost, precipitation, strong winds and high temperatures are not present.

ExperWall CM 20

COLOR OPTIONS: Grey

25

±%2 KG



**Plastering and
Masonry Mortars**

**998-2
103725**

GÜVEN MADENCİLİK İNŞAAT SAN. ve TİC. A.Ş.

SURFACE PREPARATION

- The application surface should be cleaned from dust, dirt, paint, oil and similar substances that will reduce adherence.

PREPARATION OF MIXTURE

- Using a scale, pour 4,00-4,50 liters of clean water into a clean mixing bowl.
- Slowly add ExperWall CM 20 to the bowl filled with water and mix with a low speed mixer until a homogeneous and lump free mixture is obtained.
- The mixture is allowed to rest for approximately 10 minutes, then mixed again for 1-2 minutes and made ready for application.

APPLICATION DETAILS

- The mixed mortar is applied to the surface with a trowel or a 10x10x10 mm wide notched trowel. Make sure that the mortar is applied over the entire surface.
- The bounded blocks should be fixed by ramming from the top and side.
- The bottom and side surfaces of the gas concrete blocks, which will be applied in the first row, are wetted with water and then the masonry process is started. It is not necessary to wet the gas concrete blocks during the laying of subsequent rows.
- Bonding should be done on the notched mortar within 5-10 minutes at the latest.
- The mixture in the bowl should be consumed within 1 hour.

WARNINGS

- Do not apply in weather conditions below +5°C, above +30°C, in rainy and/or windy weather.
- Avoid application in areas that are frozen, in areas with the risk of freezing within 24 hours, in conditions that may prevent the application or that may damage the surface after application.

CONSUMPTION

- 9,00-11,00 kg/m²

EQUIPMENT CLEANING

- Equipment should be cleaned with solvent immediately after use. Cured material can only be cleaned by mechanical means.

STORAGE AND SHELF LIFE

- Should be stored in its unopened original packaging, in a closed, moisture-free, dry environment, protected from frost. Products should not be overloaded in a way to damage their packaging.
- Shelf life under appropriate storage conditions is 12 months from the date of production.

SAFETY PRECAUTIONS

- During use and storage, work clothes, protective gloves and masks should be used in accordance with the rules of Occupational and Labor Health. Eye, mouth and skin contact should be avoided and the contact area should be washed with plenty of water.
- In more dangerous situations or in case of ingestion of the product, a specialist doctor should be consulted immediately. Food and beverages should not be brought into the application areas. Keep out of the reach of children. For detailed information, the Safety Data Sheet (SDS) should be consulted.

PRODUCT LIABILITY

- Güven Madencilik İnş. San. ve Tic. A.Ş., is only responsible for the quality of EXPERAS branded products. All data presented are the result of practical and scientific studies. The manufacturer cannot be held responsible except for the use of the correct products in appropriate areas and conditions.

LEGAL NOTES

ExperWall CM 20

COLOR OPTIONS: Grey

25

±%2 KG



- The information and recommendations for the use of EXPERAS branded products are provided in good faith based on technical knowledge and experience, provided that they are maintained and handled under normal conditions and in accordance with the recommendations. Along with the products, the areas of use and surfaces may vary widely. It is necessary to ensure that the correct EXPERAS branded products are applied on appropriate surfaces and under appropriate conditions. In addition, all information and instructions regarding commercial factors and technical conformity must be strictly followed. The manufacturer cannot be held responsible for any damages and problems that may occur if not complied with. The applicator/user is obliged to make the relevant checks to ensure these details. The specifications of EXPERAS branded products may be changed when necessary. The property rights of third parties must be respected. When the order is confirmed, all existing technical conditions are essential for sales and transportation.

REFERENCE STANDARDS

- TS EN 998-2



**Plastering and
Masonry Mortars**

**998-2
103725**

GÜVEN MADENCİLİK İNŞAAT SAN. ve TİC. A.Ş.